

600058

NOLTR 64-2

INITIATION OF EXPLOSIVES BY  
EXPLODING WIRES III.

- RELEASED TO DDC  
BY THE NAVAL ORDNANCE LABORATORY
- ☒ Without restrictions
  - ☐ For Release to Military and Government  
Agencies Only.
  - ☐ Approval by NOL required for release  
to contractors.
  - ☐ Approval by BuWeps required for all  
subsequent release.

NOL

17 MARCH 1964

UNITED STATES NAVAL ORDNANCE LABORATORY, WHITE OAK, MARYLAND

NOLTR 64-2

DDC

MAY 21 1964

INITIATION OF EXPLOSIVES BY EXPLODING WIRES

III. Effect of Wire Diameter on the Initiation  
of PETN by Exploding Wires

By Howard S. Leopold

ABSTRACT: The effect of wire diameter on the initiation of PETN by exploding platinum wires was investigated. A one microfarad capacitor charged to 2,000 volts was used as the energy source for exploding the wires. The diameter of the wire can be chosen so as to favor time reproducibility of explosion, reliability of effecting detonation, or vigor of the bridgewire output. The wire with the most vigorous shock output when tested in air is not necessarily the most efficient for effecting detonation when PETN is loaded on the wire.

PUBLISHED MAY 1964

EXPLOSION DYNAMICS DIVISION  
EXPLOSIONS RESEARCH DEPARTMENT  
U. S. NAVAL ORDNANCE LABORATORY  
WHITE OAK, MARYLAND

NOLTR 64-2

17 March 1964


INITIATION OF EXPLOSIVES BY EXPLODING WIRES  
III. Effect of Wire Diameter on the Initiation of PETN  
by Exploding Wires

This report is Part III of an investigation concerning the initiation of explosives by exploding wires. The work was performed under Task RUMB-4E000/212-1/P008-08-11 Problem No. 019, Analysis of Explosive Initiation.

The results should be of interest to personnel engaged in initiation research and the design of exploding bridgewire ordnance systems.

The identification of commercial materials implies no criticism or endorsement of these products by the Naval Ordnance Laboratory.

R. E. ODENING  
Captain, USN  
Commander



C. J. ARONSON  
By direction

## TABLE OF CONTENTS

	Page
INTRODUCTION	1
ELECTRICAL CIRCUITRY	1
TEST PROCEDURE	2
EXPERIMENTAL RESULTS	2
DISCUSSION	4
CONCLUSIONS	7
REFERENCES	8

## TABLE

Table	Title	Page
1	Effect of Wire Diameter	9

## ILLUSTRATIONS

Figure	Title	Page
1	Test Circuit	10
2	Test Arrangement	11
3	Smear Camera Records of Various Diameter Wires in Air	12
4	Photographic Output Comparison of Suspended Wires in Air	13
5	Photographic Output Comparison of Flush Mounted Wires in Air	14
6	Time of Burst vs Wire Diameter in Air	15
7	Explosion Loci of Various Diameter Wires in Air	16
8	Oscillograms of 0.003 Diameter Platinum Wire	17
9	Energy Deposition vs Time	18
10	Variation of Wire Resistance with Time	19
11	Energy Deposition	20
12	Energy Density	21
13	Peak and Average Power	22
14	Regions of Wire Explosion	23

# INTRODUCTION

1. This is the third report describing experimental results obtained from an investigation on the interaction between an exploding bridgewire and explosives. Previous investigation<sup>1,2</sup> had shown that circuit inductance and resistance should be kept to a minimum for effective initiation of PETN. Also, that the length of a 1-mil diameter platinum wire should be chosen so as to eliminate a definite current dwell period. In addition, it was found that secondary current pulses have little effect on whether or not detonation is produced in the PETN.

2. Bennett<sup>3</sup>, and Jones and Gallet<sup>4</sup> have shown that there is an optimum wire diameter for producing the maximum shock in air when a given wire material is exploded by a fixed firing circuit. Our original investigation was started using a platinum wire diameter of 1-mil. This diameter was arbitrarily chosen simply because it was known to explode in nominal lengths with the energy available from a 1-microfarad capacitor charged to 2,000 volts. Energy computations based on the current and voltage waveforms showed that only a small percentage of the energy stored in the capacitor was deposited in the 1-mil diameter wire. The rest of the energy is dissipated in extraneous circuit resistance or left in the capacitor. This indicated that a 1-mil diameter might not represent the best diameter that could be employed. The present investigation was concerned with determining the effect of wire diameter and learning more about the conditions that determine whether or not detonation develops.

## ELECTRICAL CIRCUITRY

3. A typical exploding bridgewire firing circuit consists of a one microfarad capacitor charged to 2,000 volts. The actual test circuit used for this investigation shown in Figure 1 is similar to that used for previous studies. The parameters for the test circuit are

$$C = 0.97 \text{ microfarad}$$

$$L = 0.58 \text{ microhenry}$$

$$R = 0.35 \text{ ohm}$$

$$V_0 = 2,000 \text{ volts}$$

Methods used for the determination of the circuit parameters are given in references 1 and 2.

\*References are given on page 8

## TEST PROCEDURE

4. The shock output of various diameter platinum bridgewires was first determined in air and then correlated with the ability to effect detonation in PETN. To determine the vigor of the output of the wire explosion, a photographic technique used by Bennett<sup>6</sup> was employed to observe the shock wave and plasma expansion of the wire. The wire was mounted in a holder as shown in Figure 2. The slit image of a smear camera was aligned perpendicularly to the wire. The image of the wire explosion reflected in a mirror provided backlighting for the event. This makes the normally non-luminous shock waves visible. Oscillograms were taken of the current and voltage waveforms concurrent with the smear photograph of the wire expansion. Resistance, power, and energy computations were made from the oscillogram readings.

5. The various diameter bridgewires were then subsequently tested for their ability to effect detonation in PETN. The test fixture and experimental methods described in reference 1 were used for observing the growth of explosion.

## EXPERIMENTAL RESULTS

6. Seven different diameters of platinum wire ranging in size from 0.0005- to 0.005-inch were tested, in the fixture shown in Figure 2, to determine the vigor of the wire explosion. The test wire, 0.050-inch long, was soldered to the upper part of the contact pins, suspended in air, and exploded. Selected photographs of the resulting explosions are shown in Figure 3. Only the upper portion of the wire explosion trace was usable because of the reflections from the contact pins which set in almost immediately in the lower portion.

7. The criterion for the vigor of wire explosion was the rate of radial expansion of the shock wave and outer plasma surface. The test results are shown graphically in Figure 4 with each curve representing the average of three shots. The curves were measured for their observable period or for a maximum of 2 microseconds. Previous data obtained with PETN loaded on the wire at a density of 1 g/cm<sup>3</sup> have shown that detonation, when it occurs, starts within one microsecond after the time of wire burst. The vigor of the wire explosion in air, as measured by the radial expansion from the time of wire burst, shows an optimum wire diameter. From the plots in Figure 4 it can be seen that the 0.003-inch diameter wire gives the most vigorous output in air, closely followed by the 0.002- and 0.0015-inch diameters.

8. Another test series was run because of the closeness of the results for the 0.0015-, 0.002-, and 0.003-inch diameter wires. The platinum wire was mounted flush on a plastic plate. A reflective mirror was not used and only the outer surface of the plasma expansion was observed. The same order of vigor was noted as shown in Figure 5. Each curve represents the average of three shots. The rate of plasma expansion is greater for this series than for the suspended wires. This is expected since the flush mounting limits the expansion region to a 180° arc.

9. It was also observed that the time to wire burst increases with increasing diameter and hence increasing mass. Nash and Olsen<sup>6</sup> have shown that there is a close to linear relationship between the cross sectional area of the wire and the time to burst at constant initial voltage. A close to linear relationship up to the 0.003-inch diameter wire was also observed in our tests. However, a definite deviation was observed with the larger diameters as shown in Figure 6. An examination of the oscillograms shows that the 0.0005-, 0.001-, 0.0015-, and 0.002-inch diameter wires explode on successively higher levels of the first current pulse. The 0.003-inch diameter wire explodes just after the first current peak. Figure 7 shows the explosion loci on an idealized\* current pulse. The 0.004-inch diameter wire does not receive enough energy to completely vaporize during the first current pulse, nor is enough energy deposited by the time current ceases to flow. Computations show that enough energy is delivered to vaporize approximately 70% of the wire and bring the remaining 30% to the boiling point. With the 0.005-inch diameter wire, the current ceases to flow after three half cycles. No shock wave is emitted and the wire breaks up into macroscopic molten particles as evidenced by the photographic traces.

10. If it is hypothesized that the vigor of the wire explosion is directly related to the ability of the wire to effect detonation, then a 0.003-inch diameter wire should be optimum for the circuit parameters employed. The ability of the wire to effect detonation in an explosive should decrease as the vigor of the wire explosion decreases. This was tested using PETN and gradually decreasing the probability of detonation by increasing the loading density of the PETN. A series of test shots was run to determine the optimum wire diameter for detonation. This method eliminated any change in the electrical parameters. The results in Table 1 show some agreement between the vigor of the wire explosion and its ability to effect detonation in PETN. Detonations could not

---

\*This is idealized because each diameter wire would produce a trace somewhat different from the traces for other diameter wires. This occurs because of the differences in wire resistance and minor changes in wire inductance.

be effected with the 0.0005-, 0.004-, and 0.005-inch diameter wires. Detonation was effected by the 0.001-, 0.0015-, 0.002-, and 0.003-inch diameter wires. The ordering, based on the ability of the wire to initiate the least sensitive PETN, shows the 0.002-inch diameter wire to be most effective followed by the 0.0015-, 0.003-, and 0.001-inch diameter wires, in that order. Comparison of this ordering with that observed in air is given below:

Ordering of Wire Diameter (inches)

<u>To Effect Detonation</u> <u>in PETN</u>		<u>Vigor of Exploding Wires</u> <u>in Air</u>
1.	0.002	0.003
2.	0.0015	0.002
3.	0.003	0.0015
4.	0.001	0.001

The wire with the most vigorous output in air is not the best for effecting detonation when surrounded by PETN. Voltage and current oscillograms obtained on the 0.003-inch diameter wire (see Figure 8) show that the current pulse dropped off rapidly when the wire exploded in contact with PETN as compared to the wire exploded in air. Wires less than 0.003-inch in diameter retain the surge. It appears that energy of electrical origin in the interval just after the wire burst can be beneficial in effecting detonation. Previously, it was not known if events up to the time of wire explosion or up to the time detonation appeared (about one microsecond later) were important.

#### DISCUSSION

11. The existence of an optimum wire diameter can be rationalized on the basis that very thin wires are poorly matched to the firing circuit. Thin wires explode in short times using a small quantity of the available stored energy during the interval of importance (time to burst plus approximately one microsecond). If the wire diameter is too large, the wire will not absorb sufficient energy to cause vaporization. This occurs even though the stored energy is sufficient to completely vaporize the wire. A comparison of energy deposition into the various diameter wires is shown in Figure 9. Energy deposition is more rapid initially with the thinner wires because of their higher initial resistance. Wires more nearly matched to the circuit initially absorb energy at a slightly lower rate than the thin wires and then, as their resistance increases, more rapidly than the thinner wires. The change of wire resistance with time is shown in Figure 10. The value of the peak resistance decreases with increasing wire



diameter. The larger wires absorb energy at a lower rate. Their resistance remains less than that inherent in the firing circuit during the period of greatest possible energy deposition (first half sine wave current pulse). The 0.004-inch diameter wire absorbs sufficient energy to give a weak explosion. Both the 0.004- and 0.005-inch diameter wires receive insufficient energy to completely vaporize the wires and can be classified as "Chace-Class I". The 0.005 inch diameter wire appears visually to break into molten droplets. This breaking occurs after the cessation of current flow since the average resistance remains almost constant at 0.1 ohm during the period of current flow.

12. Examination of energy deposition to time of wire burst, energy deposition during the microsecond interval after burst, and total energy deposition reveals no correlation with the ability of the wire to effect detonation. See Figure 11. Also, energy deposition in excess of that required for complete vaporization of the wire does not correlate. Energy density at burst shows an optimum for the 0.002-inch diameter wire which was found best for effecting detonation in PETN. However, the other diameter wires do not correlate with their respective ability to effect detonation. See Figure 12. Energy density at "burst plus one microsecond" shows that at this time the thinner the wire, the higher the energy density\*.

13. The average power and peak power for the various diameter wires was also examined. See Figure 13. Average power does not correlate with the ability to effect detonation, but peak power does show a correlation. Peak power occurs almost concurrently with the peak voltage and may indicate the most important period of electrical energy deposition. It has already been observed with the 0.003-inch diameter wire that energy after burst can be beneficial, but is not absolutely necessary.

14. The shock wave emitted by the wire is normally non-luminous. It can be rendered visible for examination by techniques such as developed by Bennett. The shock enters both the PETN crystals and interstitial air spaces. Examination of the air shock wave generated by the weakest exploding wire (0.001-inch diameter) to effect detonation reveals a velocity of 1860 meters/second. This is for a flush mounted wire and is the velocity of the air shock almost immediately after it becomes distinguishable from the plasma at approximately 0.4 microsecond. Using an interpolated value from data by R. Becker<sup>9</sup> a shock pressure of 0.037 kilobar is calculated.

---

\*Assuming all energy remains in wire material.

15. To determine whether or not compression by the shock of air trapped within the explosive could produce temperatures needed for initiation, the final temperature after adiabatic compression of a trapped gas bubble:

$$T_2 = T_1 \left[ \frac{P_2}{P_1} \right]^{\frac{\gamma-1}{\gamma}}$$

Where  $T_2$  = final temperature in degrees absolute

$T_1$  = initial temperature in degrees absolute

$P_1$  = initial pressure in bubble

$P_2$  = final pressure in bubble

$\gamma$  = ratio of specific heats

was calculated. The calculation shows that a temperature of 350°C can occur in the gas bubble under the experimental conditions. This is above the minimum temperature rise of 150°C calculated by Bowden and Yoffe<sup>9</sup> as necessary for initiation to occur. However, experiments by both Cachia and Whitbread<sup>10</sup>, and Seay and Seely, Jr.<sup>11</sup> indicate that interstitial air has no effect on the shock initiation of loosely packed granular, PETN. Cachia and Whitbread, employing a gap test, found that the critical gap remains the same whether or not interstitial air is present. Seay and Seely, using the wedge test, also found that the removal of interstitial air did not affect initiation. When they replaced interstitial air in a low density PETN with argon (for high temperatures) and methane (for low temperatures), it was found that the temperature of the interstitial gas had nothing to do with the mechanism of initiation. Their experiments further showed that a 2.5 kilobar shock pressure in the PETN pressing was barely sufficient to initiate granular PETN at a density of 1.0 g/cm<sup>3</sup>. A shock wave of the pressure encountered in the wire explosion is roughly two orders of magnitude lower than the value given by Seay and Seely. It thus appears that the shock wave is not the primary cause of initiation. It also appears that if the shock wave plays any role in the initiation it is through the medium of the PETN crystals and voids and not the interstitial gas. The largely unknown possibility of shock reflections and interactions due to interstitial spaces, crystal imperfections, and crystal voids preclude a definite conclusion on the role of the shock wave at this time.

16. It was noticed that the best firing time reproducibility is obtained when the wire explodes on the initial portion of the current pulse. The length of the block rectangle in Figure 6 indicates the time spread for each wire size.

17. It appears that the diameter of the wire should be chosen so as to explode on that portion of the current pulse best suited to give the desired effect. See Figure 14. If time reproducibility is the main consideration, the wire should explode in region A with enough of a safety factor to insure detonation. If general functioning reliability is the main consideration, region B should be chosen. If maximum wire output is desired (i.e., to break diaphragms, etc.), region C should be chosen.

#### CONCLUSIONS

1. The diameter of an exploding wire can be chosen so as to favor time reproducibility of explosion, reliability of effecting detonation, or vigor of the bridgewire output.

2. The wire with the most vigorous output in air is not necessarily the most efficient for effecting detonation in PETN.

3. Relatively thin and thick diameter wires are unable to effect detonation in PETN with the fixed value firing circuit components and voltages used.

4. For various diameter wires of constant length, peak power shows a correlation with the ability of the wire to effect detonation.

REFERENCES

1. Leopold, H., "Initiation of Explosives by Exploding Wires I. Effect of Circuit Inductance on the Initiation of PETN by Exploding Wires", NOLTR 63-159.
2. Leopold, H., "Initiation of Explosives by Exploding Wires II. Effect of Circuit Resistance on the Initiation of PETN by Exploding Wires", NOLTR 63-244.
3. Bennett, F. D., "Energy Partition in the Exploding Wire Phenomenon", BRL Report No. 1056, October 1958.
4. Jones, D. L. and Gallet, R. M. "Microwave Doppler Measurements of the Ionization Front in Cylindrical Shock Waves from Exploding Wires", in "Exploding Wires" Vol. II Plenum Press, New York, 1962.
5. Bennett, F. D., "Cylindrical Shock Waves from Exploding Wires", BRL Report No. 1035, April 1958.
6. Nash, C. P. and Olsen, C. W., "Factors Affecting the Time to Burst in Exploding Wires", in "Exploding Wires" Vol. II Plenum Press, New York, 1962.
7. Chace, W. G., and Levine, M. A., "Classification of Wire Explosions", J. Appl. Phys. 31, No. 7, 1960.
8. Lewis, B. and von Elbe, G., "Combustion, Flames, and Explosions", Academic Press, Inc. 1951.
9. Bowden, F. P., and Yoffe, A. D., "Initiation and Growth of Explosion in Liquids and Solids", Cambridge University Press, 1952.
10. Cachia, G. P., and Whitbread, E. G., "The Initiation of Explosives by Shock", Proc. Roy. Soc. A246, No. 1245, July 1958.
11. Seay, G. E., and Seely, Jr., L. B., "Initiation of a Low Density PETN Pressing by a Plane Shock Wave", J. Appl. Phys. 32, 1961.

TABLE 1  
Effect of Wire Diameter

Wire Diameter (inch)	Density of PETN (g/cm <sup>3</sup> )																	
	0.7		0.8		0.9		1.0		1.1		1.125		1.15		1.175		1.2	
	D	L	D	L	D	L	D	L	D	L	D	L	D	L	D	L	D	L
0.0005	0	3	0	2	0	2	0	2										
0.001			2	0	2	0	2	0	0	2								
0.0015			2	0	2	0	2	0	2	0	3	1	3	3	0	2	0	2
0.002			2	0	2	0	2	0	2	0	4	0	5	1	0	2	0	2
0.003			2	0	2	0	2	0	2	0	3	1	0	6	0	2	0	2
0.004			0	2	0	2	0	2										
0.005			0	2	0	2	0	2										

D = Detonation  
L = Low order




FIG. 1 TEST CIRCUIT






FIG 2 TEST ARRANGEMENT

NOLTR 64-2



0.001



0.003



0.004



0.005

0 2 4 6  
MICROSECONDS

1 CM.

FIG. 3 SMEAR CAMERA RECORDS OF VARIOUS DIAMETER WIRES IN AIR






FIG. 4 PHOTOGRAPHIC OUTPUT COMPARISON OF  
SUSPENDED WIRES IN AIR




FIG.5 PHOTOGRAPHIC OUTPUT COMPARISON OF FLUSH MOUNTED WIRES IN AIR




FIG. 6 TIME OF BURST VS. WIRE DIAMETER IN AIR




FIG. 7 EXPLOSION LOCI OF VARIOUS DIAMETER WIRES IN AIR




FIG. 8 OSCILLOGRAMS OF 0.003 DIAMETER PLATINUM WIRE




FIG. 9 ENERGY DEPOSITION VS TIME




FIG. 10 VARIATION OF WIRE RESISTANCE WITH TIME




FIG. II ENERGY DEPOSITION






FIG. 12 ENERGY DENSITY




FIG.13 PEAK AND AVERAGE POWER




FIG. 14 REGIONS OF WIRE EXPLOSION

## DISTRIBUTION

	Copies
Chief, Bureau of Naval Weapons Department of the Navy Washington 25, D. C. 20360	
DLI-3	4
RRRE-5	1
RUME-11	1
RUME-32	1
RMMO-5	1
RREN-32	1
 Director Special Projects Office Department of the Navy Washington 25, D. C.	
SP-20	1
 Superintendent Naval Post Graduate School Monterey, California	1
 Chief of Naval Research Department of the Navy Washington 25, D. C. 20360	1
 Commander U. S. Naval Ordnance Test Station China Lake, California	
Code 556	1
Technical Library	2
 Director Naval Research Laboratory Washington 25, D. C.	
Technical Information Section	2
 Commander U. S. Naval Weapons Laboratory Dahlgren, Virginia	
Technical Library	2
Weapons Laboratory	1
Terminal Ballistics Laboratory	1
Code WHR	1
 Office of Technical Services Department of Commerce Washington 25, D. C. 20230	100

Commanding Officer & Director David Taylor Model Basin Underwater Explosion Research Department Code 780 Portsmouth, Virginia	2
Commanding Officer U. S. Naval Weapons Station Yorktown, Virginia R & D Division	2
Commanding Officer U. S. Naval Ordnance Laboratory Corona, California Attn: R. Hillyer	2
Commanding Officer U. S. Naval Propellant Plant Indian Head, Maryland Technical Library	1
Commanding Officer U. S. Naval Ordnance Plant Macon, Georgia	1
Commanding Officer Naval Ammunition Depot Crane, Indiana	1
Commanding Officer U. S. Naval Ammunition Depot Navy Number Six Six (66) c/o Fleet Post Office San Francisco, California Quality Evaluation Laboratory	1
Commanding Officer U. S. Naval Ammunition Depot Concord, California Quality Evaluation Laboratory	1
Commanding Officer U. S. Naval Underwater Ordnance Station Newport, Rhode Island	1
Commanding Officer U. S. Naval Weapons Evaluation Facility Kirtland Air Force Base Albuquerque, New Mexico	1

Commanding Officer U. S. Naval Explosive Ordnance Disposal Facility Indian Head, Maryland Library Division	1
Army Material Command Department of the Army Washington 25, D. C. R & D Division	1
Commander Army Rocket & Guided Missile Agency Redstone Arsenal Huntsville, Alabama ORDXR-RH	1
Commanding General Redstone Arsenal Huntsville, Alabama Technical Library	1
Commanding Officer Picatinny Arsenal Dover, New Jersey 07801	
SMUPA-W	1
SMUPA-G	1
SMUPA-V	1
SMUPA-VL	1
SMUPA-VE	1
SMUPA-VC	1
SMUPA-DD	1
SMUPA-DR	1
SMUPA-DR-4	1
SMUPA-DW	1
SMUPA-TX	1
SMUPA-TW	1
Commanding Officer Harry Diamond Laboratory Connecticut Ave & Van Ness St., N. W. Washington 25, D. C.	
Ordnance Development Lab	1
M. Lipnick (Code 005)	1
Commanding Officer Office of Ordnance Research Box CM Duke Station Durham, North Carolina	1
Commanding Officer Engineer Research & Development Laboratory U. S. Army Ft. Belvoir, Virginia Technical Intelligence Branch	1

Commanding General Aberdeen Proving Ground Aberdeen, Maryland Attn: BRL Technical Library	1 1
Commanding General Redstone Arsenal Huntsville, Alabama Technical Library	1
Commanding General Frankford Arsenal Philadelphia 37, Pa. Library	1
Chief of Staff U. S. Air Force Washington 25, D. C. AFORD-AR	1
Commander Wright Air Development Center Wright-Patterson Air Force Base, Ohio WWAD	1 2
APGC(PGTRI, Tech. Lib.) Eglin Air Force Base, Florida 32542	1
Commanding General Air Force Systems Command Andrews Air Force Base Camp Springs, Maryland	1
Commander Air Force Cambridge Research Center L. G. Hanscom Field Bedford, Massachusetts	1
Director Applied Physics Laboratory Johns Hopkins University 8621 Georgia Avenue Silver Spring, Maryland	2
Atomic Energy Commission Washington 25, D. C. DMA	1

Director U. S. Bureau of Mines Division of Explosive Technology 4800 Forbes Street Pittsburgh 13, Pennsylvania Dr. R. W. VanDolah	1
Defense Documentation Center Cameron Station Alexandria, Virginia TIPCR	10
National Aeronautics & Space Admin. Goddard Space Flight Center Greenbelt, Maryland 20771	1
Lawrence Radiation Laboratory University of California P. O. Box 808 Livermore, California Technical Information Division Dr. M. Wilkins Dr. J. Kury	1 1 1
Director Los Alamos Scientific Laboratory P. O. Box 1663 Los Alamos, New Mexico Library	1
Sandia Corporation P. O. Box 969 Livermore, California	1
Sandia Corporation P. O. Box 5400 Albuquerque, New Mexico 87115	1
The Franklin Institute 20th & Benjamin Franklin Parkway Philadelphia 3, Pennsylvania (Mr. Gunther Cohn)	1
Aerojet-General Corporation Ordnance Division Downey, California , Attn: Dr. H. Fisher	1
Alleghaney Ballistics Laboratory Cumberland, Maryland	1



Flare-Northern Division Atlantic Research Corporation 19701 W. Goodvale Road Saugus, California	1
Atlas Powder Company Tamaqua, Pennsylvania	1
Flare-Northern Division Atlantic Research Corporation P. O. Box 175 West Kanover, Massachusetts Mr. J. A. Smith, Sec. Off.	1
Bernite Powder Company Saugus, California Attn: Mr. L. LoFiego	1
Hercules Powder Company Port Ewen, New York C. Wood G. Scherer	1 1
Martin Company 815 Elwell Street Orlando, Florida M. Hedges	1
Thiokol Chemical Corporation Redstone Arsenal Huntsville, Alabama	1
Stanford Research Institute Poulter Laboratories Menlo Park, California	1
Thiokol Chemical Corporation Hunter-Bristol Division Bristol, Pennsylvania	1
McCormick Selph Association Hollister Airport Hollister, California	1

NOLTR 64-2

Librascope Division 670 Arques Avenue Sunnyvale, California Attn: Mr. T. Parker	1
Lockheed Aircraft Corporation P.O. Box 504 Sunnyvale, California	1
Beckman & Whitley Research and Development Division 993 San Carlos Avenue San Carlos, California	1
General Laboratory Associates 17 E. Railroad Street Norwich, N. Y.	1
National Aeronautics & Space Administration Manned Spacecraft Center Houston, Texas, Attn: Mr. W. H. Simmons	1
R. H. Stresau Laboratory Spooner, Wisconsin	1
Special Devices Incorporated 16830 W. Placerita Canyon Road Newhall, California	1
Hi-Shear Corporation 2600 W. 247th Street Torrance, California	1
Unidynamics Universal Match Corp. P.O. Box 2990 Phoenix, Arizona	1
Atlas Chemical Industries, Inc. Valley Forge Industrial Park Valley Forge, Pennsylvania (19481)	1



<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 64-2) INITIATION OF EXPLOSIVES BY EXPLODING WIRES. III. EFFECT OF WIRE DIAMETER ON THE INITIATION OF PETN BY EXPLODING WIRES, by Howard S. Leopold. 17 Mar. 1964. 9p. illus., tables. BuNaps task NUME-45000/212-1/FO08-08-11.</p> <p>UNCLASSIFIED</p> <p>The effect of wire diameter on the initiation of PETN by exploding platinum wires was investigated. The diameter of the wire can be chosen so as to favor time reproducibility of explosion, reliability of effecting detonation, or vigor of the bridgewire output.</p>	<p>1. Explosives - Initiation 2. PETN 3. Wire, Exploding I. Title II. Leopold, Howard S. III. Project IV. Effect ... wire</p>	<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 64-2) INITIATION OF EXPLOSIVES BY EXPLODING WIRES. III. EFFECT OF WIRE DIAMETER ON THE INITIATION OF PETN BY EXPLODING WIRES, by Howard S. Leopold. 17 Mar. 1964. 9p. illus., tables. BuNaps task NUME-45000/212-1/FO08-08-11.</p> <p>UNCLASSIFIED</p> <p>The effect of wire diameter on the initiation of PETN by exploding platinum wires was investigated. The diameter of the wire can be chosen so as to favor time reproducibility of explosion, reliability of effecting detonation, or vigor of the bridgewire output.</p>	<p>1. Explosives - Initiation 2. PETN 3. Wire, Exploding I. Title II. Leopold, Howard S. III. Project IV. Effect ... wire</p>	<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 64-2) INITIATION OF EXPLOSIVES BY EXPLODING WIRES. III. EFFECT OF WIRE DIAMETER ON THE INITIATION OF PETN BY EXPLODING WIRES, by Howard S. Leopold. 17 Mar. 1964. 9p. illus., tables. BuNaps task NUME-45000/212-1/FO08-08-11.</p> <p>UNCLASSIFIED</p> <p>The effect of wire diameter on the initiation of PETN by exploding platinum wires was investigated. The diameter of the wire can be chosen so as to favor time reproducibility of explosion, reliability of effecting detonation, or vigor of the bridgewire output.</p>	<p>1. Explosives - Initiation 2. PETN 3. Wire, Exploding I. Title II. Leopold, Howard S. III. Project IV. Effect ... wire</p>
<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 64-2) INITIATION OF EXPLOSIVES BY EXPLODING WIRES. III. EFFECT OF WIRE DIAMETER ON THE INITIATION OF PETN BY EXPLODING WIRES, by Howard S. Leopold. 17 Mar. 1964. 9p. illus., tables. BuNaps task NUME-45000/212-1/FO08-08-11.</p> <p>UNCLASSIFIED</p> <p>The effect of wire diameter on the initiation of PETN by exploding platinum wires was investigated. The diameter of the wire can be chosen so as to favor time reproducibility of explosion, reliability of effecting detonation, or vigor of the bridgewire output.</p>	<p>1. Explosives - Initiation 2. PETN 3. Wire, Exploding I. Title II. Leopold, Howard S. III. Project IV. Effect ... wire</p>	<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 64-2) INITIATION OF EXPLOSIVES BY EXPLODING WIRES. III. EFFECT OF WIRE DIAMETER ON THE INITIATION OF PETN BY EXPLODING WIRES, by Howard S. Leopold. 17 Mar. 1964. 9p. illus., tables. BuNaps task NUME-45000/212-1/FO08-08-11.</p> <p>UNCLASSIFIED</p> <p>The effect of wire diameter on the initiation of PETN by exploding platinum wires was investigated. The diameter of the wire can be chosen so as to favor time reproducibility of explosion, reliability of effecting detonation, or vigor of the bridgewire output.</p>	<p>1. Explosives - Initiation 2. PETN 3. Wire, Exploding I. Title II. Leopold, Howard S. III. Project IV. Effect ... wire</p>	<p>Naval Ordnance Laboratory, White Oak, Md. (NOL technical report 64-2) INITIATION OF EXPLOSIVES BY EXPLODING WIRES. III. EFFECT OF WIRE DIAMETER ON THE INITIATION OF PETN BY EXPLODING WIRES, by Howard S. Leopold. 17 Mar. 1964. 9p. illus., tables. BuNaps task NUME-45000/212-1/FO08-08-11.</p> <p>UNCLASSIFIED</p> <p>The effect of wire diameter on the initiation of PETN by exploding platinum wires was investigated. The diameter of the wire can be chosen so as to favor time reproducibility of explosion, reliability of effecting detonation, or vigor of the bridgewire output.</p>	<p>1. Explosives - Initiation 2. PETN 3. Wire, Exploding I. Title II. Leopold, Howard S. III. Project IV. Effect ... wire</p>